



Standard Specification for Roofing Slate¹

This standard is issued under the fixed designation C 406; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (*e*) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of slate for use as roof shingles.

1.2 Slates not included in this specification are those containing soft carbonaceous ribbons. The wide variation in physical properties and composition of such ribbon slates render their service life uncertain under some conditions of use.

2. Referenced Documents

2.1 *ASTM Standards:*

C 119 Definitions of Terms Relating to Dimension Stones²

C 120 Methods of Flexure Testing of Slate (Modulus of Rupture, Modulus of Elasticity)²

C 121 Test Method for Water Absorption of Slate²

C 217 Test Method for Weather Resistance of Slate²

3. Terminology

3.1 *Definitions*—Definitions shall be in accordance with Definitions C 119.

3.2 *Description of Terms Specific to This Standard:*

3.2.1 *service life*—a period of time over which the slate material may be expected to require no repair or replacement due to weathering.

3.2.2 *ribbons*—narrow bands of carbonaceous material, darker in color than the surrounding slate. These ribbons are inclusions of the original beds and are softer and less durable than the surrounding material.

4. Classification

4.1 Roofing slate shall be classified by grade in accordance with the physical requirements of Table 1.

4.2 Expected service life of the various grades, depending on geographic location and environmental exposure, is as follows:

Grade	Service Life (in years)
Grade S ₁	over 75
Grade S ₂	40 to 75
Grade S ₃	20 to 40

¹ This specification is under the jurisdiction of ASTM Committee C-18 on Dimension Stones and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved Aug. 25, 1989. Published October 1989. Originally published as C 406 - 57 T. Last previous edition C 406 - 84 (1988).

² *Annual Book of ASTM Standards*, Vol 04.08.

5. Ordering Information

5.1 *Color*—The following color nomenclature is commonly used:

Black	Mottled purple and green
Blue black	Green
Gray	Purple variegated
Blue gray	Red
Purple	Weathering green (changes to buff or brown)

5.2 *Standard Roofs*—Sloping roofs utilizing a nominal thickness of ³/₁₆ to ¹/₄ in. (4.8 to 6.4 mm), are known as standard roofs. These shingles shall be rectangular unless otherwise specified. These shingles shall be machine punched or drilled for two nails located for proper headlap.

5.3 *Textural Roofs*—Sloping roofs utilizing various sizes, thicknesses, textures, and colors for architectural effects, are known as textural roofs. These shingles shall be machine punched or drilled for two nails located for proper headlap.

5.4 *Graduated Roofs*—Sloping roofs utilizing a greater range of sizes, thicknesses, and exposed lengths of shingles, are known as graduated roofs. The slates are arranged on the roof so that the thickest and longest occur at the eaves and gradually diminish in size and thickness toward the ridges. These shingles shall be machine punched or drilled for two nails located for proper headlap.

6. Physical Requirements

6.1 Slate supplied under this specification shall conform to the physical requirements listed in Table 1.

6.2 Broken corners on the exposed ends of slates may be considered cause for rejection when either the base or leg of the right triangular piece broken off is greater than

TABLE 1 Physical Requirements

Classification	Modulus of Rupture Across the Grain, min, psi (MPa) ^A	Absorption, max, % ^B	Depth of Softening, max, in. (mm) ^C
Grade S ₁	9000 (62)	0.25	0.002 (0.05)
Grade S ₂	9000 (62)	0.36	0.008 (0.20)
Grade S ₃	9000 (62)	0.45	0.014 (0.36)

^A See Methods C 120.

^B See Test Method C 121.

^C See Test Method C 217.

1 1/2 in. (38.1 mm).

6.3 The curvature of shingles shall not exceed 1/8 in. in 12 in. (1 mm in 100 mm). Curved slate shall be sheared and punched to permit it to be laid with the convex side up.

6.4 “Knots” and “knurls” are rounded defects which affect the smoothness of split. They may be acceptable on the exposed portion of the top face but on other parts may prevent close contact of shingles. Shingles having knots or knurls on the covered portions may be rejected if the protuberance projects more than 1/16 in. (1.6 mm) beyond the split surface.

6.5 Slate shall be free from ribbons.

6.6 Not more than 1% of broken slates, including those having cracks materially precluding ringing when sounded, shall be accepted.

6.7 Face dimensions shall not differ from those specified by more than 1/8 in. (3.2 mm).

7. Sampling

7.1 Samples for testing of characteristics and physical properties, if required, shall be representative of the slate to be used.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1916 Race St., Philadelphia, PA 19103.